

## BlackTop RC

## DP504

### Rust Converting Primer

A water based, tannic acid-free rust converter which can convert rust to an inert, black iron oxide barrier layer within minutes of application. Can be topcoated with both waterborne and solventborne coatings. Maintains good adhesion with topcoats.

### Surface Preparation

Remove all loose rust, salt, mill scale, grease, oil and other deposits. Apply rust converter to dry, tight rust.

### Application Method

Shake or stir the product well before using. Some phase separation may occur during long term storage but product quality is not compromised. Thinning is not required. Product can be sprayed, rolled or brushed. The rust starts to turn black within a few minutes of application. A second coat can be applied to ensure complete conversion of all rust.

Allow 30-45 minutes of dry time before applying second coat. Allow up to 48 hours for complete cure of the rust converter before applying a top coat.

### Soap and Water Cleanup

Diversified Chemical Products  
4124 Northeast Riverside Street  
Riverside, Missouri 64150  
United States of America  
+1.816.472.5515 phone  
[www.diversifiedchemicalproducts.com](http://www.diversifiedchemicalproducts.com)

### Physical Properties

Form.....	Liquid
Odor.....	Mild Sweet
Color.....	Milky Green
Clarity.....	Opaque
Sediment.....	Negligible
Shelf Life.....	1 Year
Cold Stability.....	Keep from Freezing
pH.....	2.5-3.0
Specific Gravity.....	1.09
Pounds/Gallon.....	9.07
Viscosity.....	75cps@25°C
Solids.....	42.6%byWt



**DCP**  
Diversified Chemical Products